


Marley Solvent-Based Plaster Primer

An Alkaline Resistant Plaster Primer for interior and exterior application on new cement plaster, fibre cement, bricks and composition boarding.



SPREAD RATE: 4-6m² per litre – depending on porosity of surface

APPLICATION: Brush, Roller, Spray

CLEANING: Mineral Turpentine

DRYING: Touch Dry: 4 Hours

RECOAT: 16 Hours

COATS: 1-2 Coats



ADVANTAGES:

- > Exceptional Obliteration and Coverage.
- > Excellent Opacity.
- > Excellent Adhesion.

MarleyRoofing

> Alkaline Resistant.

FEATURES:

- > Matt finish suitable for Interior and Exterior use.
- > Available in White.
- > Available in 5L & 20L.

SURFACE PREPARATION:

NEW SURFACES

New cement plaster:

- Ensure the surface is in sound condition before paint is applied. Allow cement plaster to cure and dry for 28 days to avoid moisture entrapment or any paint failure.
- Remove plaster spatter and dust. Apply two coats MARLEY SOLVENT-BASED PLASTER PRIMER and allow to dry.

New fibre-cement, bricks and composition boarding:

 Remove dust and loose particles. Apply MARLEY SOLVENT-BASED PLASTER PRIMER and allow recommended drying time.

PREVIOUSLY PAINTED SURFACES:

Old paint in sound condition:

- Clean surface and rinse thoroughly. Ensure that the old coating adheres to the substrate. No need to apply MARLEY SOLVENT-BASED PLASTER PRIMER if surface is sound.
- Apply two coats of finishing product.





Previously painted with solvent-based product:

• Apply MARLEY UNIVERSAL UNDERCOAT and allow recommended drying time.

Powdery surface:

• Sand down and remove dust. Apply MARLEY BONDING LIQUID and allow recommended drying time before applying intermediate and final coats.

Fungal growth:

- Remove fungal growth by using a quality Fungal Wash.
- Rinse thoroughly and allow to dry.

PREVIOUSLY PAINTED SURFACES IN POOR CONDITION

• Strip and treat as new work.

Gypsum plaster

GYPSUM PLASTER IS NOT RECOMMENDED FOR EXTERIOR USE!

Interior: DO NOT SAND GYPSUM PLASTER! Apply MARLEY SOLVENT-BASED PLASTER PRIMER and allow 12 hours to dry. Apply two coats of finishing products.

Filling

• Use suitable and approved filler.

APPLICATION

- Stir thoroughly before use with a flat paddle.
- Application: Roller, brush or air assisted spray
- Thinning: Mineral Turpentine Diluted 10% with Mineral Turpentine for better penetration on new cement plaster and for spray application
- Cleaning: Mineral Turpentine
- Coats: 1 to 2 coats

GENERAL DATA

- Touch dry: 4 hours @ 23°C
- Recoating time: 16 hours @ 23°C
- Spreading rate: 4 6m² / litre, depending on porosity of surface and application



TECHNICAL DATA

Viscosity: 78 ± 2KuS.G.: 1.23 ± 0.01

MarleyRoofing

DFT: N/A

• Flash point: Not determined.

PACKAGING AND STORAGE

- Packaging: 5L and 20L (only white)
- Storage: Keep away from direct sunlight, heat and severe cold
- Keep container sealed and avoid contact with moisture!

HEALTH AND SAFETY

- Ensure good ventilation during application and drying.
- Avoid contact with skin and eyes.
- Do not smoke, eat or drink while using the product. Wash hands before eating.
- Store in a cool dry place.
- Do not dispose of into natural waterways or drainage system.
- Keep out of reach of children.
- Consult a general practitioner in case of contact with eyes or ingestion.
- Rain may cause paint failure whilst applying.
- Please see Material Safety Data Sheet for more information.

ADDITIONAL SAFETY, HEALTH & ENVIRONMENTAL INFORMATION

EMERGENCY NUMBER: 076 102 3432



This Product may be flammable, containing toxic substances!



Human Health Hazards: Keep out of reach of children! If accidentally swallowed seek medical advice immediately! Ensure application is done in a well-ventilated area to minimize the effects of exposure to vapours, fumes and mists that may cause irritation to eyes and sinuses. To minimize direct contact, it is our recommendation to wear suitable protective clothing, safety eyewear and protective gloves, as wells as respiratory protective equipment in enclosed spaces that lack adequate ventilation.

Environmental Hazards: Could have undesirable environmental side effects, therefore do not empty into drains and watercourses. Contain and collect spillage with absorbent material. Dispose of according to local regulations.

Handling: Keep container tightly closed. Eating, drinking and smoking should be prohibited in area where this material is handled, stored and processed. Always comply with health and safety regulations.

Storage & Transportation: Always store and transport in original container, in a secure upright position, in a cool, well-ventilated area away from incompatible materials and ignition sources. Containers which have been opened must be carefully resealed and kept upright to prevent leakage.

Storage Conditions: Store under cool dry conditions away from direct sunlight, heat and extreme cold.

GUARANTEE

Together with Marley's finishing coats, namely, Marley M11 Ultra with a 10-year guarantee, Marley M22 Ultimo with a 15-year guarantee or Marley M22 Classic with a 22-year guarantee, MARLEY SOLVENT-BASED PLASTER PRIMER applied correctly in accordance with this datasheet, forms part of a full coating system guarantee.

To register your guarantee, simply call Marley Roofing's Technical Paint Department within 30 days of purchase or send us your guarantee application via our website. Basic requirements to register your guarantee include supplying us with your contact details, the site details, purchase details, applicator's details (person or contractor who painted), batch number/s and related products used.

Your successful application will receive a Guarantee Reference Number that you should record and keep in a safe place, together with your purchase slip for future reference.

For more information as well as terms and conditions of the guarantee, please visit www.marleyroofing.co.za or contact Marley Roofing's Paint Technical Helpline 076 102 3432.



STANDARD DISCLAIMER PERTAINING TO THIS TECHNICAL DATASHEET (TDS)

The recommendations contained herein are given in good faith and meant to guide the specifier or user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Marley Roofing's control.

Important Note: Technology may change with time, necessitating changes to this Technical Data Sheet (TDS).

It is the responsibility of the user to ensure that the latest TDS is being used for reference. Marley Roofing Technical Data Sheets are available on our website www.marleyroofing.co.za or please contact us at 010 600 0284.

Email info@marley.co.za

MarleyRoofing

Marley SA (Pty) Ltd trading as Marley Roofing, is a member of the Ubora Group, the industrial division of Kutana Group of Companies.

VERSION: 01. 01_03_2023

*THIS DATASHEET SUPERSEDES ALL PREVIOUS VERSIONS

CONTACT DETAILS:

Call: 010 600 0284

Email: info@marley.co.za

Web: www.marleyroofing.co.za or scan QR code below:



Follow us:





https://www.facebook.com/MarleyRoofingZA https://www.linkedin.com/company/27058241/